



## Renewable Lubricants, Inc.

Distributed By: DM's Bio-Based Fluid Supply Inc.  
10 McEwan Dr. W, Unit 4B  
Bolton, ON, Canada L7E 1H1  
Voice: 905.951.1100 Fax: 905.951.2100  
[www.dmsbiobased.ca](http://www.dmsbiobased.ca)

### **Bio-AW/AL™ Hydraulic Press Oils** **ISO 32, 46, 68**



### *"Bio-based Lubricants that Perform Like Synthetics"*

Bio-AW/AL™ Hydraulic Press Oils are ultimately biodegradable<sup>1</sup> vegetable based formulas that replace mineral oil based hydraulic fluids in demanding press hydraulic systems. Bio-AW/AL™ Hydraulic Press Oils are formulated to perform in hydraulic systems that require Anti-Wear (AW), Anti-Leak (AL), anti-rust, anti-oxidation, anti-foam, and demulsibility properties. Bio-AW/AL™ Hydraulic Press Oils contain the same performance benefits and additive technology as the Bio-Ultimax™ 1000 Hydraulic Fluids with the addition of the anti-leak and/or non-drip performance. They are highly inhibited against moisture and rusting in both fresh and sea water and pass both A and B Sequences of the ASTM D-665 Turbine Oil Rust Test. Incorporating the super high viscosity index of the Stabilized\* High Oleic Base Stocks (HOBS) into the formula, increases the viscosity index past synthetic levels (Energy Conserving Formulas). A zinc-free (ashless) additive system has also been developed that is environmentally friendly and meets or exceeds pump requirements.

Bio-AW/AL™ Hydraulic Press Oils are designed for use in mobile and stationary hydraulic vane, piston, and gear-type pumps when used in accordance with the equipment manufacturer. **Very little wear was encountered, 0 to 25mg (Pass), in accelerated bio-based tests using Denison T-5D, Vickers 20VQ, 35VQ-25 (M-2950-S), and V-104C (ASTM D-2882) pump stand tests at pressures and temperatures ranging from 2000 to 3000 psi and from 150<sup>0</sup> to 210<sup>0</sup> F.** The anti-wear performance exceeds the load stage 10 in the FZG (DIN 51354) requirements for US Steel 136, DIN 51524, and GM (LS-2). They also meet the requirements for ashless GL-3 gear oils in reduction units and gear sets where they meet the viscosity ranges.

The super high viscosity index of the HOBS naturally improves the thermal shear stability of the formula and increases load capacity. The HOBS's extremely low volatility increases the flash and fire safety features in the formula. They are formulated to provide seal conditioning for longer seal life and to reduce oil leakage from the system. Bio-AW/AL™ Hydraulic Press Oils should be used in hydraulic systems where low toxicity, and BIODEGRADABILITY properties are required. Base oils and additives in these products pass and exceed the acute toxicity (LC-50) criteria adopted by the US Fish and Wildlife Service and the US EPA. Bio-AW/AL™ Hydraulic Press Oils are ENVIRONMENTALLY RESPONSIBLE lubricants that are formulated from renewable agricultural plant resources. We believe Earth's environmental future rests in the use of renewable materials.

STABILIZED by Renewable Lubricants\* is RLI's trademark on their proprietary and patented anti-oxidant, anti-wear, and cold flow technology. High Oleic Base Stock (HOBS) are agricultural vegetable oils. This Stabilized technology allows the HOBS to perform as a high performance formula in high and low temperature applications, reducing oil thickening and deposits.

<sup>1</sup> Ultimate Biodegradation (Pw1) within 28 days in ASTM D-5864 Aerobic Aquatic Biodegradation of Lubricants

Patented Product: US Patent 6,383,992, US Patent 6,534,454 with additional Pending and Foreign Patents

\* Trademark of Renewable Lubricants, Inc.

Copyright 1999 Renewable Lubricants, Inc.

**Availability** **F.O.B. :Bolton, ON, Canada**

**5 Gallon Pails** **Drums** **Bulk**

## Bio-AW/AL™ Hydraulic Press Oils ISO 32, 46, 68

The test data below show that the Bio-AW/AL™ Hydraulic Press Oils provide high performance in a wide variety of stationary and transportation equipment that operate in broad ranges of environmental conditions. In equipment operating outside, wear from poor cold temperature pumpability, surge loads, moisture, and dusty environments are more prominent. Bio-AW/AL™ Hydraulic Press Oils are formulated to improve performance in equipment that requires excellent anti-wear, anti-leak, hydrolytic stability, and cold temperature pumpability as low as -35°C.

TYPICAL SPECIFICATIONS	METHOD	ISO 32	ISO 46	ISO 68	Spec. Requirements
Specific Gravity @ 15.6°C	ASTM D-287	<b>0.874</b>	<b>0.876</b>	<b>0.886</b>	Report
API Gravity @ 15.6°C	ASTM D-287	<b>30.4</b>	<b>30.0</b>	<b>28.2</b>	Report
Viscosity @ 40°C	ASTM D-445	<b>30.87</b>	<b>43.8</b>	<b>64.1</b>	Note 1
Viscosity @ 100°C	ASTM D-445	<b>6.9</b>	<b>9.67</b>	<b>12.5</b>	Note 1
Viscosity @ -15°C, Brookfield	ASTM D-2983	<b>not complete</b>	<b>1100 cP</b>	----	Note 1
Viscosity @ -25°C, Brookfield	ASTM D-2983	<b>1,200 cP</b>	<b>3,000 cP</b>	----	Note 1
Viscosity @ -30°C MRV TP1	ASTM D-4684	<b>4,500 cP</b>	<b>8,000 cP</b>	----	10W= <60,000
Viscosity @ -35°C MRV TP1	ASTM D-4684	<b>7,500 cP</b>	----	----	5W= <60,000
Viscosity Index	ASTM D-2270	<b>184</b>	<b>216</b>	<b>198</b>	90 (min)
Pour Point	ASTM D-97	<b>-40°C</b>	<b>-36°C</b>	<b>-30°C</b>	Note 1
Flash Point (COC)	ASTM D-92	<b>236°C</b>	<b>243°C</b>	<b>251°C</b>	198°C (min)
Fire Point (COC)	ASTM D-92	<b>260°C</b>	<b>268°C</b>	<b>274°C</b>	218°C (min)
Hydrolytic Stability, Copper Wt. Loss (mg) Copper Appearance Water Layer	ASTM D-2619	<b>0.0139</b> <b>1B</b> <b>&lt;4</b>	<b>0.0208</b> <b>1B</b> <b>&lt;4</b>	<b>0.0208</b> <b>1B</b> <b>&lt;4</b>	0.2 Report 4
Foam Sequence I, II, III (10 min)	ASTM D-892	<b>0 Foam</b>	<b>0 Foam</b>	<b>0 Foam</b>	0 Foam
Rust Prevention Distilled Water Syn. Sea Water	ASTM D-665	<b>Pass</b> <b>Pass</b>	<b>Pass</b> <b>Pass</b>	<b>Pass</b> <b>Pass</b>	Pass Pass
Copper Corrosion Strip 3hr @ 100°C	ASTM D-130	<b>1B</b>	<b>1B</b>	<b>1B</b>	DIN 51524 2(max)
Rotary Bomb Oxidation, (minutes)	ASTM D-2272	<b>360</b>	<b>360</b>	<b>360</b>	USS 120 (min)
Oxidation Stability (Pressure Differential Scanning Calorimeter) min	ASTM D-5483 Modified	<b>70.0 (165°C)</b>	<b>70.0 (165°C)</b>	<b>70.0 (165°C)</b>	Note 2
Neutralization Number mg KOH/g	ASTM D-974	<b>&lt;0.4</b>	<b>&lt;0.4</b>	<b>&lt;0.4</b>	1.5 (max)
Swell of Synthetic NBR-L Rubber, % (Avg.) Volume Change (%) Shore A Hardness Change (%)	DIN 53538, Part 1	<b>6.0</b> <b>-4</b>	<b>6.0</b> <b>-4</b>	<b>6.0</b> <b>-4</b>	0 to 12 0 to -7
Filterability A-No Water (s) (Avg) B-2% Water (s) (Avg)	Denison TP 02100 HF-0 Requirement	<b>113</b> <b>187</b>	<b>268</b> <b>271</b>	<b>335</b> <b>449</b>	600 (max) 2xA (max)
Demulsibility, ML Oil/Water/Emulsion	ASTM D-1401	<b>40/ 40/ 0</b>	<b>40/ 40/ 0</b>	<b>40/40/0</b>	40/37/3 (max)
4-Ball Wear, 1h, 167°F, 1200 RPM, 40 kg	ASTM D-4172	<b>0.3 – 0.4</b>	<b>0.3 – 0.4</b>	<b>0.3 – 0.4</b>	USS 127 0.5 (max)
FZG Test	DIN 51354	<b>12</b>	<b>12</b>	<b>12</b>	US.Steel 10 (min)
<b><u>Biodegradation Classification</u></b>	ASTM D-5864	Ultimate PW1	Ultimate PW1	Ultimate PW1	Ultimate PW1
<b><u>Note 1 Viscosity Sufficient for Application</u></b>					
<b><u>Note 2 Not Required</u></b>					